



TEST DATA

ANTI-CORROSION SPRAYS (TINNED WIRE)

TREATMENT	RESISTANCE	GENERAL APPEARANCE	WIRE CONDITION	WIRE UNDER TERMINAL SCREW
NOALOX	< 0.05 ohms	Good	Good	Poor
NO-OX-ID	< 0.05 ohms	Very good	Good	Very good
BOESHIELD	< 0.05 ohms	Very poor	Very poor	Poor
WATERPROOF GREASE	< 0.05 ohms	Poor	Poor	Good
CORROSION BLOCK	< 0.05 ohms	Good	Good	Good

After 12-months in the test chamber, the thicker No-Ox-Id did a good job of warding off corrosion. The spray-on Corrosion Block also provided good long-term protection.